

Ramsay Cobalt

Selected Diamond Drill Intervals

DDH	From	To	Length	Cu %	Co%
M04-01	13.8	14.9	1.1	0.849	0.024
M04-01	33.3	36.3	3	0.213	0.190
M04-01	33.3	34.2	0.9	0.168	0.367
M04-02	24.9	35	10.1	0.073	0.023
M04-02	32.6	33.1	0.5	0.160	0.245
M04-03	23.9	24.4	0.5	0.16	0.01
M04-04	24	51.5	27.5	0.229	0.166
M04-04	43	47.8	4.8	0.019	0.352
M04-04	45	47.8	2.8	0.037	0.721
M04-04	48.8	50.5	1.7	0.990	0.018
M04-05	11	12.9	1.9	0.469	0.044
M04-05	28.4	34.5	6.1	0.052	0.314
M04-05	32.5	34.5	2	0.031	0.808
M04-05	95.4	104.7	9.3	0.111	0.028
M04-05	102.7	103.7	1	0.597	0.011
M04-06	20	21	1	0.114	0.314
M04-06	36	130	94	0.097	0.035
M04-06	37	38	1	0.570	0.140
M04-06	62	63	1	0.065	0.226
M04-06	85	86	1	0.116	0.886
M04-06	101	102.4	1.4	0.950	0.009
M04-07	64	68	4	0.161	0.037
M04-08	5.5	10	4.5	0.040	0.008
M04-08	54	58	4	0.195	0.035
M04-09	10	16	6	0.070	0.019